

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
8 July 2004 (08.07.2004)

PCT

(10) International Publication Number
WO 2004/056459 A1

(51) International Patent Classification⁷: **B01D 69/08**,
D01D 5/24, B01D 71/06

[DE/DE]; Rosengarten 2, D-72406 Bisingen (DE). **BUCK**,
Reinhold [DE/DE]; Kirchstrasse 24, 88422 Alleshhausen
(DE).

(21) International Application Number:
PCT/SE2003/001985

(74) Agents: **AHLBERG**, Camilla et al.; Gambro Intellectual
Property Department, P.O. Box 10101, S-220 10 Lund
(SE).

(22) International Filing Date:
17 December 2003 (17.12.2003)

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC,
SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA,
UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
0203857-8 20 December 2002 (20.12.2002) SE

(71) Applicant (*for all designated States except US*): **GAM-
BRO LUNDIA AB** [SE/SE]; P.O. Box 10101, S-220 10
Lund (SE).


(84) Designated States (*regional*): ARIPO patent (BW, GH,
GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,
ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE,
SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA,
GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): **GÖHL, Hermann**

[Continued on next page]

(54) Title: PERMSELECTIVE MEMBRANE AND PROCESS FOR MANUFACTURING THEREOF



(57) Abstract: The present invention relates to a membrane being suitable for, for example, hemodialysis. Said membrane comprises at least one hydrophobic polymer and at least one hydrophilic polymer. According to the present invention the outer surface of the hollow fiber has pores in the range of 0,5-3 µm and the numbers of said pores in the outer surface are in the range of 10, 000 to 150, 000 pores per mm², preferably in the range of 18, 000 to 100, 000 pores per mm² and most preferably in the range of 20, 000 to 100, 000 pores per mm². The present invention further relates to a process for the preparation of said membrane and use of said membrane in hemodialysis, hemodiafiltration and hemofiltration, and in dialysis and filtration in general, for example in water purification or dehydration.



Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.